

ESKA™ Plastic Optical Fiber: CK100

Manufactured by Mitsubishi Chemical Corporation

Marketed and sold by Mitsubishi International PolymerTrade Corporation

January 2010

Structure		
Core Material	Polymethyl Methacrylate Resin (PMMA)	
Cladding Material	Fluorinated Polymer	
Core Refractive Index	1.49	
Refractive Index Profile	Step Index	
Numerical Aperture	0.5	
	Unit	Typical
Core Diameter	μm	2,450
Overall Diameter	μm	2,500
Approximate Weight (g/m)	6.0	

Packaging	
Spool Length (m)	250
Net weight on spool (kg)	1.5
Coil Weight (kg)	-
Carton Size (mm)	405 X 410 X 75
Carton Weight (kg)	1.8
Master Carton	10 coils

Performance		Criteria for Acceptance and/or [Test Conditions]	Unit	Values
Storage and Operation Temperature		No deterioration in optical properties [in a dry atmosphere] *	°C	-55 ~ 70
Operating Temperature in a Moist Atmosphere		No deterioration in optical properties [under 95% RH] **	°C	Max.60
Optical Properties	Transmission Loss [650nm Collimated Light]	[Standard Condition] [10m-1m cutback]	dB/km	Max.200
Mechanical Characteristics	Minimum Bend Radius	Loss increment =< 0.5dB [quarter bend]	mm	Min.100
	Tensile Strength	Tensile force at yield point [JIS C 6861]	N	Min.400

CK100-C Cut Bristles		
Straight, one-meter long fibers with no memory curve, manufactured in the U.S. using ESKA™		
Diameter(μm)	Length (mm)	Number bristles per pack
500	1,000	500 +0/-3%

Applications: Lighting
CK grade fibers are typically used for lighting environments and illuminating applications.

Product Testing
The CK-Series of fibers is a tested and qualified, but has unspecified tolerances and typical values. The information contained in this document should, therefore, only be used as a guide.

Notes: Performance tested in conditions under 25°C unless otherwise indicated

* Attenuation increase shall be <10% after 1,000 hours

** Attenuation increase shall be <10% after 1,000 hours, except when due to absorbed water

The information contained herein is presented as a guide to product selection. It is subject to change without notice, and should not be regarded as a representation, warranty or guarantee with regard to the quality, characteristics or use of this product