ESKA[™] Plastic Optical Fiber: CK80

Manufactured by Mitsubishi Chemical Corporation

Marketed and sold by Mitsubishi International PolymerTrade Corporation

January 2010

Structure					
Core Material	Polymethyl Methacrylate Resin (PMMA)				
Cladding Material	Fluorinated Polymer				
Core Refractive Index	1.49				
Refractive Index Profile	Step Index				
Numerical Aperture	0.5				
	Unit	Typical			
Core Diameter	μm 1,960				
Overall Diameter	μm	μm 2,000			
Approximate Weight (g/m)	3.8				

Packaging				
Spool Length (m)	250			
Net weight on spool (kg)	1.0			
Coil Weight (kg)	-			
Carton Size (mm)	405 X 410 X 75			
Carton Weight (kg)	1.3			
Master Carton	10 coils			

Straight, one-meter long fibers with no memory curve, manufactured in the U.S. using ESKATM

Diameter(µm)	Length (mm)	Number bristles per pack
500	1,000	500 +0/-3%

Applications: Lighting

CK grade fibers are typically used for lighting environments and illuminating applications.

Product Testing

The CK-Series of fibers is a tested and qualified, but has unspecified tolerances and typical values. The information contained in this document should, therefore, only be used as a guide.

Approximate Weight (g/m)		3.8	3.8		
Performance		Criteria for Acceptance and/or [Test Conditions]	Unit	Values	
Storage and Operation Temperature		No deterioration in optical properties [in a dry atmosphere] *	°C	-55 ~ 70	
Operating Te Atmosphere	mperature in a Moist	No deterioration in optical properties [under 95% RH] **	°C	Max.60	
Optical Properties	Transmission Loss [650nm Collimated Light]	[Standard Condition] [10m-1m cutback]	dB/km	Max.200	
Mechanical Character- istics	Minimum Bend Radius	Loss increment =< 0.5dB [quarter bend]	mm	Min.80	
	Tensile Strength	Tensile force at yield point [JIS C 6861]	N	Min.260	

Notes: Performance tested in conditions under 25°C unless otherwise indicated

* Attenuation increase shall be <10% after 1,000 hours

** Attenuation increase shall be <10% after 1,000 hours, except when due to absorbed water

The information contained herein is presented as a guide to product selection. It is subject to change without notice, and should not be regarded as a representation, warranty or guarantee with regard to the quality, characteristics or use of this product

Mitsubishi International PolymerTrade Corporation

2 Penn Plaza East, 11th Floor, Newark, NJ 07105