ESKA[™] Premier PVC Jacketed Optical Fiber Cord: GHV4002

Manufactured by Mitsubishi Chemical Corporation

Marketed and sold by Mitsubishi International PolymerTrade Corporation

January 2010

| Structure | | | | | |
|----------------------------------|--------------------------------------|---------|--|--|--|
| Core Material | Polymethyl Methacrylate Resin (PMMA) | | | | |
| Cladding Material | Fluorinated Polymer | | | | |
| Core Refractive Index | 1.49 | | | | |
| Refractive Index Profile | Step Index | | | | |
| Numerical Aperture | 0.5 | | | | |
| | Unit | Typical | | | |
| Core Diameter | μm | 980 | | | |
| Cladding Diameter | μm | 1,000 | | | |
| Number of Fibers | 2 | | | | |
| Jacket Dimension - Minor Axis | mm | 2.2 | | | |
| Jacket Dimension – Major Axis | mm | 4.3 | | | |
| Approximate Weight | g/m | 11.0 | | | |

| Packaging | | | | |
|---------------------------|----------------------------|--|--|--|
| Spool Length (m) | 500 | | | |
| Net weight on spool (kg) | 6.7 | | | |
| Spool Weight (kg) | 1.2 | | | |
| Carton Size (mm) | 365 X 365 X 160 | | | |
| Carton Weight (kg) | 7.3 | | | |
| Master Carton | 5 spools | | | |
| Jacket | | | | |
| Jacket | | | | |
| Jacket Color and Material | Gray, Polyvinylchloride | | | |
| | | | | |

| Performance | | Criteria for Acceptance and/or [Test Conditions] | Unit | Values |
|--|---|---|-------|------------------|
| Operation Temperature | | No deterioration in optical properties [in a dry atmosphere]* | °C | - 55 ~ 85 |
| Operating Temperature in a Moist Atmosphere | | No deterioration in optical properties [under 95% RH] ** | °C | Max.75 |
| Optical Properties | Transmission Loss [650nm Collimated Light] | [25°C 50% RH] | dB/km | Max.170 |
| | | [Operation Temperature] | dB/km | Max.190 |
| Mechanical Character- istics | Minimum Bend Radius | Loss increment =< 0.5dB [a quarter bend]*** | mm | Min.25 |
| | Repeated Bending Endurance | Loss increment =< 1 dB [in conformity to the JIS C 6861]**** | Times | Min.5,000 |
| | Tensile Strength | [Tensile force at yield point; in conformity to the JIS C 6861] | N | Min.140 |
| | Twisting Endurance | Loss Increment =< 1 dB [sample length: 1m, Tensile Force: 4.9N] | Times | Min.2 |
| | Impact Endurance | Loss Increment =< 1 dB [in Conformity to the JIS C 6861] | N⋅m | Min.0.4 |

Notes: Performance tested in conditions under 25°C unless otherwise indicated.

- * Attenuation increase shall be <10% after 1,000 hours.
- ** Attenuation increase shall be <10% after 1,000 hours,
- except when due to absorbed water.
- *** In the direction of the minor axis.
- **** Bend Angle +/-90 $^{\circ}$, Bend Radius 15mm, Tension 1,000g.

Applications

The GH-Series of single-jacketed cables are typically used as data transfer media.

The information contained herein is presented as a guide to product selection. It is subject to change without notice, and should not be regarded as a representation, warranty or guarantee with regard to the quality, characteristics or use of this product

